

WHAT IS CLAIMED IS:

- Sub
A2
1. A method of lithographic printing comprising the steps of:
 - (i) unwinding a web of a flexible lithographic base from a supply spool, the lithographic base having a hydrophilic surface;
 - (ii) wrapping the lithographic base around a cylinder of a printing press;
 - (iii) applying on the lithographic base an image-recording layer which is removable in a single-fluid ink or can be rendered removable in a single-fluid ink by exposure to heat or light;
 - (iv) image-wise exposing the image-recording layer to heat or light;
 - (v) processing the image-recording layer by supplying single-fluid ink, thereby obtaining a printing master;
 - (vi) printing by supplying single-fluid ink to the printing master which is mounted on a plate cylinder of the printing press; and
 - (vii) removing the printing master from the plate cylinder.
 2. The method according to claim 1 wherein the image-recording layer is a non-ablative image-recording layer which is removable with the single-fluid ink before exposure to heat or light and is rendered less removable by exposure to heat or light.
 3. The method according to claim 2 wherein the image-recording layer comprises hydrophobic thermoplastic polymer particles.
 4. The method according to claim 3 wherein the image-recording layer further comprises a hydrophilic binder.
 5. The method according to claim 2 wherein the image-recording layer comprises an aryldiazosulfonate polymer.
 6. The method according to claim 1 wherein the supply spool is located within the plate cylinder.
 7. The method according to claim 1 wherein step (vii) is carried out by winding the printing master on an uptake spool which is located within the plate cylinder.

10068312.020502

8. The method according to claim 1 wherein the flexible lithographic base comprises a plastic support, a thin aluminum support or a laminate of plastic and thin aluminum.
9. The method according to claim 1 wherein the single-fluid ink is an emulsion comprising:
- (i) a continuous phase comprising an acid-functional vinyl resin; and
 - (ii) a discontinuous phase comprising a liquid polyol.
- 10 The method according to claim 9 wherein the vinyl resin is a branched acid-functional vinyl resin having a number average molecular weight of between about 1000 and about 15000 and a weight average molecular weight of at least about 100000.

205020 2728901